

Application Number 10/594936  
Response to the Office Action dated December 11, 2008

RECEIVED  
CENTRAL FAX CENTER  
APR 03 2009

**Amendments to the Claims:**

This listing of claims will replace all prior versions and listings of claims in the application.

**Listing of Claims:**

1. (Currently Amended) An article with an organic-inorganic composite film, the article comprising a substrate and an organic-inorganic composite film that is formed on a surface of the substrate and contains an organic material and an inorganic oxide,

~~wherein the organic-inorganic composite film contains a hydrophilic organic polymer as the organic material,~~

the organic-inorganic composite film contains a network structure of silica in a form of siloxane polymer as the inorganic oxide,

the organic-inorganic composite film contains the silica as its main component, and

the organic-inorganic composite film contains a hydrophilic organic polymer as the organic material in the network structure of silica, and

the organic-inorganic composite film does not separate from the substrate after the Taber abrasion test prescribed in Japanese Industrial Standards R 3212 that is carried out with respect to a surface of the organic-inorganic composite film, the Taber abrasion test being carried out at a rotation number of 1000 with a load of 500 g being applied.

2. (Original) The article according to claim 1, wherein the organic-inorganic composite film has a thickness of more than 250 nm but not more than 5  $\mu\text{m}$ .

3. (Original) The article according to claim 2, wherein the organic-inorganic composite film has a thickness of more than 300 nm but not more than 5  $\mu\text{m}$ .

4. (Original) The article according to claim 3, wherein the organic-inorganic composite film has a thickness of 1  $\mu\text{m}$  to 5  $\mu\text{m}$ .

Application Number 10/594936

Response to the Office Action dated December 11, 2008

5. (Original) The article according to claim 1, wherein a portion that has been subjected to the Taber abrasion test has a haze ratio of 4% or lower after the Taber abrasion test.

6. (Cancelled)

7. (Original) The article according to claim 1, wherein the organic-inorganic composite film contains phosphorus.

8. (Cancelled)

9. (Previously presented) The article according to claim 1, wherein the hydrophilic organic polymer includes a polyoxyalkylene group.

10. (Original) The article according to claim 1, wherein the organic-inorganic composite film contains fine particles.

11. (Original) The article according to claim 10, wherein the content of the fine particles is at least 1 mass%, and a portion that has been subjected to the Taber abrasion test has a haze ratio of 4% or lower after the Taber abrasion test.

12 - 21. (Cancelled)

22. (Previously presented) The article according to claim 1, wherein the substrate is a glass sheet.

23 - 24. (Cancelled)

25. (Withdrawn – currently amended) An article with an organic-inorganic composite film, the article comprising a substrate and an organic-inorganic composite

Application Number 10/594936

Response to the Office Action dated December 11, 2008

film that is formed on a surface of the substrate and contains an organic material and an inorganic oxide,

wherein the organic-inorganic composite film contains a network structure of silica in a form of siloxane polymer as the inorganic oxide,

the organic-inorganic composite film contains the silica as its main component,

the organic-inorganic composite film contains no fine particles,

the substrate is a glass sheet,

the organic-inorganic composite film contains the organic material in the network structure of silica, and

the organic-inorganic composite film does not separate from the substrate after the Taber abrasion test prescribed in Japanese Industrial Standards R 3212 that is carried out with respect to a surface of the organic-inorganic composite film, the Taber abrasion test being carried out at a rotation number of 1000 with a load of 500 g being applied.

26. (Cancelled)

27. (Currently Amended) An article with an organic-inorganic composite film, the article comprising a substrate and an organic-inorganic composite film that is formed on a surface of the substrate and contains an organic material and an inorganic oxide,

wherein the organic-inorganic composite film contains a network structure of silica in a form of siloxane polymer as the inorganic oxide,

the organic-inorganic composite film contains the silica as its main component,

the organic-inorganic composite film contains fine particles of electrically conductive oxide,

the organic-inorganic composite film contains the organic material in the network structure of silica, and

the organic-inorganic composite film does not separate from the substrate after the Taber abrasion test prescribed in Japanese Industrial Standards R 3212 that is carried out with respect to a surface of the organic-inorganic composite film, the Taber abrasion test being carried out at a rotation number of 1000 with a load of 500 g being applied.

Application Number 10/594936  
Response to the Office Action dated December 11, 2008

28. (Cancelled)